

Thin Pour, Rapid Cure, High Strength, Epoxy Grout

Technical Bulletin # 618 I

## Product Description

CHOCKFAST RED SG is a three component, high strength, 100% solids epoxy grouting compound which is used to grout large machinery and to support soleplates in all types of foundation designs with clearances as little as 1" (25mm). CHOCKFAST RED SG has extremely high physical properties and negligible shrinkage, making it ideal for final positioning of critically aligned equipment within close tolerances. Skid mounted compressors, extruders, turbines, pumps, motors and crane rails are just a few types of equipment supported on CHOCKFAST RED SG. When using CHOCKFAST RED SG for crane rail applications expansion joints may be placed every 10' (3m).

## Use & Benefits

CHOCKFAST RED SG has the following advantages when compared to conventional cementitious grouts:

- Impervious to oil and chemical attack
- Pre-packaged unit
- Higher physical strengths
- Unaffected by weathering and freeze/thaw cycling
- Cures at least three times as quickly
- Grout machinery in final aligned position
- Strong bond to metal and concrete
- Superior resistance to fatigue

CHOCKFAST RED SG contains no non-reactive diluents which could interfere with the curing mechanism or which could cause material loss during or after cure. Machinery may be positioned at its final elevation before pouring because the shrinkage is negligible. Critical alignments are maintained during machinery operation due to CHOCKFAST RED SG's high dimensional stability and resistance to creep and vibration.

## Design Considerations

For design considerations and application details, please request Bulletin No. 643 or contact ITW Polymer Technologies' Engineering Services Department.

## Application Instructions

CHOCKFAST RED SG may be mixed with a contractor's hoe and wheelbarrow or in a portable mortar mixer. Thoroughly mix hardener with resin first before mixing in aggregate. Where a very flowable mix is required, the aggregate content may be reduced accordingly. Contact the CHOCKFAST Representative or ITW Polymer Technologies when reducing aggregate.

CHOCKFAST RED SG is quick curing relative to cement grouts, but the cure is thermally gentle. This allows thick pours to be made without causing the stress cracks often associated with a hot curing epoxy grout. CHOCKFAST RED SG may be used in any thickness greater than 1" (25mm); however, individual pours should generally not exceed 4" (100mm) in thickness and 5' (1.5m) in length.

CHOCKFAST RED SG cure rates and flowability will be enhanced somewhat if material temperatures are warmer than the existing ambient conditions listed above. It is always a good idea to keep CHOCKFAST RED SG materials in a well-protected area until the job site is fully prepared for mixing and placement.

NOTE: Standard CHOCKFAST RED is available and allows deep single pours to 18" (450mm) for concrete reconstruction. Please see Bulletins No. 642 and 617.

**ITW POLYMER TECHNOLOGIES**

130 Commerce Drive • Montgomeryville, PA 18936 • 215-855-8450 • Fax 215-855-4688  
www.chockfast.com



ITW Polymer Technologies  
Registered to ISO 9001:2009  
File No. A3790



ITW Performance Polymer Europe  
ISO 9001:2009  
Q 05-120

## Physical Properties

COMPRESSIVE STRENGTH	18,120 psi (1174 kg/cm <sup>2</sup> )	ASTM C-579 (MOD)
COMPRESSIVE MODULUS OF ELASTICITY	1.97 x 10 <sup>6</sup> psi (138535 kg/cm <sup>2</sup> )	ASTM C-579 (MOD)
LINEAR SHRINKAGE	Not Measurable	ASTM D-2566
COEFFICIENT OF LINEAR THERMAL EXPANSION	10.8 x 10 <sup>-6</sup> /°F @ 32°F to 140°F (19.4 x 10 <sup>-6</sup> /°C @ 0°C to 60°C)	ASTM D-696
FLEXURAL STRENGTH	4,800 psi (340 kg/cm <sup>2</sup> )	ASTM C-580
FLEXURAL MODULUS OF ELASTICITY	2.62 x 10 <sup>6</sup> psi (184,200 kg/cm <sup>2</sup> )	ASTM C-580
TENSILE STRENGTH	2,130 psi (150 kg/cm <sup>2</sup> )	ASTM D-638
IZOD IMPACT STRENGTH	7.2 in.lbs./in. (0.32 Newton m/cm)	ASTM D-258
FIRE RESISTANCE	Self-extinguishing	ASTM D-635
SERVICE TEMPERATURE	Up to 140°F (60°C)	
SPECIFIC GRAVITY	2.24	

## Product Information

COVERAGE	1.6 ft <sup>3</sup> (45.3 Liters)
APPLICATION TEMPERATURE	55°F (13°C) to 95°F (35°C)
UNIT PACKAGING	Resin (NH): 2.59 gal (9.05 L) in a 3 gal pail Hardener (H): 0.43 gal (1.63 L) in a 1 gal can Aggregate: (4) bags - 46 lb. (21 kg) / bag
UNIT WEIGHT	Resin: 23.3 lbs. (10.6 kg) Hardener: 3.6 lbs. (1.6 kg) Aggregate: 184 lbs (84 kg)
SHIPPING WEIGHT	213 lbs. (96.6 kg)
CURE TIME (approximate)	24 to 48 hours @ 70°F (21°C)
POT LIFE	1 hour @ 70°F (21°C)
CLEAN UP	IMPAX IXT-59 or similar epoxy solvent
SHELF LIFE	Two years in dry storage

## Reference

For design considerations and application details please request Bulletin No. 642 or contact ITW Polymer Technologies' Engineering Services Department.

## Date

06/2006

**General:** Every reasonable effort is made to insure the technical information and recommendations on these data pages are true and accurate to the best of our knowledge at the date of issuance. However, this information is subject to change without notice. Prior versions of this publication are invalid with the release of this version. Products and information are intended for use by qualified applicators that have the required background, technical knowledge, and equipment to perform said tasks in a satisfactory manner. Consult your local distributor for product availability, additional product information, and technical support.

**Warranty:** ITW Polymer Technologies, a division of Illinois Tool Works Inc., warrants that its products meet their printed specifications. This is the sole warranty. This warranty expires one year after product shipment.

**Warranty Claims:** If any product fails to meet the above, ITW Polymer Technologies will, at its option, either replace the product or refund the purchase price. ITW Polymer Technologies will have no other liability for breach of warranty, negligence, or otherwise. All warranty claims must be made in writing within one year of the date of shipment. No other claims will be considered.

**Disclaimer:** ITW Polymer Technologies makes no other warranty, expressed or implied, and specifically disclaims any warranty of merchantability or fitness for a particular purpose.

Suggestions concerning the use of products are not warranties. The purchaser assumes the responsibility for determining suitability of products and appropriate use. ITW Polymer Technologies' sole liability, for breach of warranty, negligence or otherwise, shall be the replacement of product or refund of the purchase price, at ITW Polymer Technologies' election. Under no circumstances shall ITW Polymer Technologies be liable for any indirect, incidental or consequential damages.

**Modification of Warranty:** No distributor or sales representative has the authority to change the above provisions. No change in the above provisions will be valid unless in writing and signed by an officer or the Technical Director of ITW Polymer Technologies. No term of any purchase order shall serve to modify any provision of this document.

**Mediation and Arbitration:** If any dispute arises relating to products or product warranties, either the purchaser or ITW Polymer Technologies may a) initiate mediation under the then current Center for Public Resources (CPR) Model Procedure for Mediation of Business Disputes, or b) initiate a non-binding arbitration under the rules of the American Arbitration Association for the resolution of commercial disputes.